

## Material specification sheet

### Saarstahl - 20Mn5

Material No.:                      Former brand name:                      International steel grades:

**1.1133**

**Atrix 101**

**BS: 120M19**

**AFNOR: 20M5**

**SAE: 1022, 1518**

**Material group:**                      High temperature constructional steel according to DIN EN 10269

Chemical composition: (Typical analysis in %)	C	Si	Mn	Cr	other
	0,20	0,50	1,15	-	-

**Application:**                      High temperature constructional weldable steel for forgings and pipes of boiler plants and for constructions of apparatus, pressure vessels and pipelines.

**Hot forming and heat treatment:**                      Hardening: 870 - 900°C  
Tempering: 580 - 680°C

#### Mechanical Properties:

**Condition of delivery:**                      Quenched and tempered

Effective wall thickness [mm]	<=250	250 - 500
0,2% proof stress R <sub>p0,2</sub> [N/mm <sup>2</sup> ]	min. 295	min. 275
Tensile strength R <sub>m</sub> [N/mm <sup>2</sup> ]	490 - 640	490 - 640
Fracture elongation longitudinal A <sub>5</sub> [%]	min. 22	min. 21
Fracture elongation tangential A <sub>5</sub> [%]	min. 19	min. 18
Fracture elongation transverse A <sub>5</sub> [%]	min. 15	min. 14
Notch impact energy longitudinal DVM [J]	min. 48	min. 48
Notch impact energy tangential DVM [J]	min. 34	min. 34
Notch impact energy transverse DVM [J]	min. 24	min. 24