

Material specification sheet

Saarstahl - 20MoCrS4

Material No.:	Former brand name:	International steel grades:
1.7323	Mo 20	BS: AFNOR: SAE:

Material group: Case hardening steels according to DIN EN 10084

Chemical composition: (Typical analysis in %)	C	Si	Mn	Cr	Mo	S	other
	0,20	0,25	0,75	0,40	0,45	0,020 0,035	(Pb)

Application: Alloyed case hardening steel for wear resisting automobile and gear parts with a core tensile strength of 800 - 1100 N/mm² and high toughness for gears, crown wheels, primary shafts etc. Suitable for direct hardening.

Hot forming and heat treatment:	Forging or hot rolling:	1150 - 850°C
	Normalising:	840 - 870°C/air
	Soft annealing:	650 - 700°C/furnace
	Carburising:	880 - 980°C
	Core hardening:	860 - 900°C/oil
	Intermediate annealing:	650 - 700°C
	Case hardening:	780 - 820°C/oil
	Tempering:	150 - 200°C

Mechanical Properties:	Treated for cold shearability, +S:	max. 255 HB
	Soft annealed, +A:	max. 207 HB
	Treated for strength, +TH:	156 - 207 HB
	Treated for ferrite and pearlite structure and hardness range, +FP:	140 - 187 HB

after hardening and tempering at 200°C:

Diameter d [mm]	d ≤ 16	16 < d ≤ 40	40 < d ≤ 100
Tensile strength R _{pm} [N/mm ²]	min. 900	min. 800	-